

TEST LABORATORY

15708 Pomerado Road, Suite N208, Poway, CA 92064 Phone (858) 451-8868 - Fax (858) 451-9268

E-mail: sfi@sfifoundation.com

SFI Spec 3.2A Test R & D

Company Name: Heliotextil.SA Report Number: 19-347-2 Address:Rua dos Combatentes do Ultramar PO box 467 Date of Report: 08/01/19

City, State, Zip: 3701-914 S João da Madeira Purchase Order No.: VAT 500133263 Contact: Anabela Guimarães Phone: 00351256201100

Type of Test: **Flammability**

Part Number/Name: Heat Press Mobil 1 Logo LITE No.086

50% Aramid / 50% Viscose 250g/m² ± 5%

Specification/Revision: SFI Spec 3.2A Driver Suits/Effective: March 27, 2013

Test Procedure: Paragraph 5.1.1

Date of Test: 07/25/19

Requirements:

The average after flame time shall be 2.0 seconds or less. The average char length shall be six (6) inches or less. Any melting or dripping of the material is cause for failure.

Results:

Sample	After Flame Time (Sec.)	Char Length (Inches)
1	0.3	0.5
2	0.4	0.6
3	0.3	0.4
4	0.2	0.5
5	0.3	0.3
Average	0.3	0.46

This report applies only to the actual samples tested. SFI Laboratory does not certify, warrant or quarantee any products manufactured by others. Samples discarded within 1 year unless otherwise requested in writing by manufacturer.

SFI LABORATORY

Michael J. Sherbo Laboratory Manager