



15708 Pomerado Road, Suite N208, Poway, CA 92064
Phone (858) 451-8868 – Fax (858) 451-9268
E-mail: sfi@sifoundation.com

TEST LABORATORY

SFI Spec 3.2A Test R & D

Company Name: Heliotextil.SA Report Number: 19-522-2
Address: Rua dos Combatentes do Ultramar PO box 467 Date of Report: 11/21/19
City, State, Zip: 3701-914 S João da Madeira, Portugal Purchase Order No.: Sub form 10/21/19
Contact: Anabela Guimarães Phone: 00351256201100

Type of Test: **Flammability**
Part Number/Name: **Heat Press Mobil 1 Logo 1 Layer**
100% Nomex Type N 327 150g/cm²
Specification/Revision: SFI Spec 3.2A Driver Suits/Effective: March 27, 2013
Test Procedure: Paragraph 5.1.1
Date of Test: 10/31/19

Requirements:

The average after flame time shall be 2.0 seconds or less. The average char length shall be six (6) inches or less. Any melting or dripping of the material is cause for failure.

Results:

Sample	After Flame Time (Sec.)	Char Length (Inches)
1	0.1	1.1
2	0.1	2.5
3	0.2	2.6
4	0.1	1.4
5	0.2	2.9
Average	0.14	2.1

This report applies only to the actual samples tested. SFI Laboratory does not certify, warrant or guarantee any products manufactured by others. Samples discarded within 1 year unless otherwise requested in writing by manufacturer.

SFI LABORATORY

Michael J. Sherbo
Laboratory Manager